


# FIBRANgyps FLEX



## Product Description

Gypsum based board (plasterboard) standard type A , CE marked according to the standard UNI EN 520, with one decorative ivory face .

Available in thickness : 6mm(BA6).

## Applications

Suitable for the construction of curved elements, such as inner walls, linings, ceilings and decorations.

Features	U. M.	Value	Standard
Edge	-	BA tapered edge	EN 520
Width	mm	1200	EN 520
Thermal conductivity (at 10°C)	W/m K	$\lambda_d = 0,25$ theoretical value	EN 10456
Reaction to fire	Class	A2-s1,d0	EN 520
Specific Heat Capacity	kJ/kg K	$c_p = 1,0$ theoretical value	EN 10456
Water vapor resistance factor	-	$\mu = 10$ in dry area theoretical value	EN 10456

Type	Thickness [mm]	Weight [kg/m <sup>2</sup> ]	Length [m]	Flex. long. [N]	Flex. trasv. [N]
BA6	6	5,5	3,0	≥ 258	≥ 100

Marking on the board back:

FIBRANgyps FLEX – sp.6 mm - CE – A - EN 520 A2-S1,d0(B) - date and time of production- D.o.P number

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavor to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to materials' use. For more information visit the web site [www.fibran.it](http://www.fibran.it) .

Date 31/07/2018

FIBRAN S.p.A. via Fiasella 5/11 16121 GENOVA Italy - ph. +39 010 25466.1 fax +39 010 25466.949 - [www.fibran.it](http://www.fibran.it) – [tech@fibran.it](mailto:tech@fibran.it)